

# Ultraure A-80 Topcoat

**Non-Slip \* Heavy Duty \* Two-Part UV Resistant Protective Coating**

## Description

A tough, fast curing, non-slip, aliphatic polyurethane coating designed for protection of Chemind Ultraure A-80 and Chemspray membrane systems in exposed situations. Ultraure A-80 Topcoat is UV resistant - it provides a durable, non-slip trafficable finish to roof and deck areas.

## Uses

Ultraure A-80 Topcoat is used for colour-fast, non-slip surface to Ultraure A-80 waterproof membrane or Chemspray elastomers on exposed car-park decks, plant room floors, roofs, box-gutters, balconies, terraces, etc.

It may be used as a stand-alone durable finish on walkways, steps, ramps, etc., as a functional, decorative, colour-fast protective coating, in exposed external situations.

## Features

- Simple application, easy to use and fast cure
- UV Resistant and foot trafficable
- Quick access for trades
- Permanently flexible - total adhesion
- Immediate Resistance to rain damage
- High chemical resistance
- May be line marked with fast dry paints

Contact Chemind Technical Department for any specific requirements on 1800 33 44 44.

## Typical Properties

Drying Time @ 25°C	2 hours
Shore Hardness	80°A (+/- 5)
Tensile Strength (AS1145)	2 MPa
Elongation (AS1145)	350%
UV Resistance (System)	Excellent

## Preparation

Surface must be clean and dry.

## Application

First, mix Resin to incorporate non-slip additive, then add Hardener component. Blend carefully with electric mixer.

Mix full 20kg sets. If small quantity is needed mix ratio is Hardener:Resin by weight 4.7:1. Use clean dry container.

Apply in two coats by brush or roller – apply second coat in cross direction to the first to give a uniform finish.

For spraying use a single wet-on-wet spray application.

Do NOT use mixed product once it has become thick and stringy, it must be discarded. Do NOT add solvent.

## Coverage

Ultraure A-80 Topcoat – 0.3 kg/m<sup>2</sup> (min 0.15mm DFT).

## Packaging

Ultraure A-80 Non-Slip Topcoat Resin – 16.5 kg pails

Ultraure A-80 Hardener – 3.5 kg cans

## Clean Up

Use Chemind GP Solvent or methylated spirits before curing. Exercise care when using solvents and review all MSDS before use.

## Shelf Life

Sealed pails of have a shelf life of approx. 6 months, but once opened may become solid.



**HEAD OFFICE**  
74 Annie Street  
ROCKLEA QLD 4106  
AUSTRALIA  
Ph: (+617) 3255 5755  
Fax: (+617) 3255 5991  
ABN: 63 250 804 992